

## CLASSIFICATION

EN 1600 : E 20 10 3 B 22      Werkstoff-Nr : 1.4431  
AWS A5.4 : E308 Mo-15

## GENERAL DESCRIPTION

LSN-308Mo is a basic coated electrode. It gives a filler metal of the Cr-Ni-Mo type that is high (2.5 %) in Mn content. Weld beads are highly resistant to sudden impact and cracking due to heat effect.

## APPROVALS

GOST, SEPRO, TSE

## APPLICATIONS AND MATERIALS TO BE WELDED

AS P-308Mo is used for forming a buffer layer for hardfacing and joining of armour steel plates, heat treatable steels, different type steels and for steels with poor weldability.

There is no need to apply heat treatment to armour steel plates before or after the welding. Interpass temperature during welding should not exceed 120°C. It is also used to form a buffer layer for stress relief before hardfacing applications.

## CHEMICAL COMPOSITION (W%), TYPICAL, ALL WELD METAL

C	Si	Mn	Cr	Ni	Mo
0.05	0.35	2.50	19.00	10.00	2.50

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Yield Strength	: 420 N/mm <sup>2</sup>
Tensile Strength	: 620 N/mm <sup>2</sup>
Elongation (L=5d)	: 38 %
Impact (ISO-V)	: 100 J (+20°C)

## WELDING PARAMETERS / PACKING AND DIAMETER INFORMATIONS / WELDING POSITIONS

Current Type and Polarity : DC (+)

Diameter [ mm ]	Length [ mm ]	Current [ A ]	Electrode Weight [ g/100 pcs ]	Box Weight [ kg ] Quantity [ pcs/box ]	Export Box Box Weight [ kg ]
3.25	300	80 - 110	2855	2.0 / 70	2.0
4.00	350	110 - 140	5095	2.3 / 45	2.5



**Liability** : All information in this data sheet is based on the best available knowledge, is subject to change without notice and can only be considered as suitable for general guidance.  
**Fumes** : Consult information on Welding Safety Sheet, available upon request.

### Lion International U.K (M.E.) Limited

Monomark House, 27 Old Gloucester Street, London WC1N 3XX, United Kingdom.  
T: +44 20 74198760 F: +44 20 78319489 E: info@lionintweld.co.uk

### Lion International Middle East FZC

P.O. Box 41654, W/H No. 1K-01/4, Hamriyah Free Zone, Sharjah, UAE.  
T: +971 6 5260461 F: +971 6 5260561 E: info.me@lionintweld.co.uk