

CLASSIFICATION

EN 1600: E 18 8 Mn B 22 DIN 8555: E8 - 200 CKZ
AWS A5.4: (E307-15) Werkstoff-Nr : 1.4370

GENERAL DESCRIPTION

LSN-307 is a basic coated electrode. It gives an austenitic filler metal of the Cr-Ni type that is high (6.0 %) in Mn content. Weld beads are highly resistant to oxidation at operating temperatures up to 850°C and also to acids.

APPROVALS

CE, GOST, SEPRO, TSE, TÜV

GL

4370

CHEMICAL COMPOSITION (W%), TYPICAL, ALL WELD METAL

C	Si	Mn	Cr	Ni
0.10	0.50	6.00	18.00	9.00

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Yield Strength	: 420 N/mm ²
Tensile Strength	: 640 N/mm ²
Elongation (L=5d)	: 35 %
Impact (ISO-V)	: 100 J (+20°C) 75 J (-60°C)
Hardness	: 200 HB (as welded) 400 HB (after cold working)

APPLICATIONS AND MATERIALS TO BE WELDED

LSN-307 can be used for welding hardenable steels (alloyed or unalloyed), Mn steels, armour plates, rail steels, stainless chromium steels, tool steels and steels with poor weldability. Building up of parts operating under impact, high pressure and cavitation; surface build up of water turbine vanes; build up of valve seats and joining and building up of rail switches are among its usage areas. LSN-307 can also be used for forming buffer layer passes before hardfacing applications having a chromium carbide structure.


The lowest possible welding current should be selected to avoid the overheating of the electrode during welding. For hard Mn- steels, weld beads should be forged.

	EN 10088-1/-2	W. Nr	EN 10088-1/-2	W. Nr
Heat Resistant	X6 Cr 13	1.4000	X10 CrAlSi 7	1.4713
Stainless Steels	X12 Cr 13	1.4006	X10 CrAlSi 13	1.4724
	X20 Cr 13	1.4021		
	X17 CrNi 16 2	1.4057		

WELDING PARAMETERS / PACKING AND DIAMETER INFORMATIONS / WELDING POSITIONS

Current Type and Polarity : DC (+)

Diameter [mm]	Length [mm]	Current [A]	Electrode Weight [g/100 pcs]	Box Weight [kg] Quantity [pcs/box]	Export Box Box Weight [kg]
2.50	250	50 - 80	1590	1.6 / 100	1.5
3.25	300	80 - 110	3030	2.3 / 75	2.0
4.00	350	100 - 140	5100	2.3 / 45	2.5
5.00	350	140 - 160	7060	2.5 / 35	2.5



Liability : All information in this data sheet is based on the best available knowledge, is subject to change without notice and can only be considered as suitable for general guidance.
Fumes : Consult information on Welding Safety Sheet, available upon request.

Lion International U.K (M.E.) Limited

Monomark House, 27 Old Gloucester Street, London WC1N 3XX, United Kingdom.
T: +44 20 74198760 F: +44 20 78319489 E: info@lionintweld.co.uk

Lion International Middle East FZC

P.O. Box 41654, W/H No. 1K-01/4, Hamriyah Free Zone, Sharjah, UAE.
T: +971 6 5260461 F: +971 6 5260561 E: info.me@lionintweld.co.uk